

## TECHNICAL DATA SHEET

### Heavy Slack Wax

**Note:**

- Slack Wax Can Be A Blended Component In PVC Industry As Lubricant
- Feed Stock For Production Of Paraffin Wax
- Dust Suppressant
- Vast Application In Waterproofing Industry.
- Used As A Blending Agent In The Production Of Petrolatum And Microcrystalline Waxes
- An Excellent Waterproofing Agent In Wood And MDF Industries

No	Specification	Result	Test Method
1	Melting Point °C (Cst)	Approx. 56-65	ASTMD 87
2	Oil Content % WT	12 - 18	ASTM D 721
3	KIN. Viscosity 100 °C	6 - 7.5	ASTM D 445
4	Color 70 °C(Max)	1/5	ASTM D 1500

